

Technical data sheet

Diessner Penetrating Primer (Diessner Tiefgrund)

Aqueous primer



Aqueous, fine-particle penetrating primer

- Very low-odour
- Minimum emissions, free from solvents and plasticisers
- High penetration depth
- Good surface strengthening
- Saponification-stable
- Environmentally friendly
- Easy to spread
- Fine-particle

Application

Transparent primer on an aqueous hydrosol basis. For interior use, for regulating the absorbency of highly absorbent or varyingly absorbent substrates. For exterior use, for the regulation of absorbency of surfaces that absorb again. Suitable substrates are brickwork, plasters (DIN EN 998-1/DIN V 18550 MG P Ic- P IV), concrete, structured plasters, old paint that can be coated, etc.

Technical data

Binding agent base	Plastic dispersion in accordance with DIN 55947
Colour	Transparent
Container size	5 and 10 litre container
Storage	Store in a cool, frost-free environment. Seal opened containers well and consume in short order. Unopened containers can be kept for a minimum of 24 months.
Coverage	Depending on the absorbency of the substrate, approx. 150-200 ml/m ² per coat on a smooth substrate, substantially more on textured surfaces. Test any object-specific deviations with a trial coat patch.
Product code for paints and varnishes	M-DF 01

Technical data sheet

Diessner Penetrating Primer (Diessner Tiefgrund)

Aqueous primer

VOC content	Class h type wb, VOC limit from 2010 = 30 g/l, VOC content <1 g/l
Hazard identification	Not applicable
Declaration of ingredients	Acrylic resin hydrosol, water, additives, preservative.- Advice for people allergic to isothiazolinone is available on telephone number: +49 (0)30 60 000 249
Special notes	When using in a spraying process, do not breathe in the spray mist and use breathing apparatus during spraying work. Always read and note the label and product information prior to use. Do not allow the paint to enter drainage systems, waterways or soil. Carefully cover all surfaces that are not to be coated. Rinse any paint sprayed onto surfaces with water whilst still wet. For more information, see EC safety datasheet.
Disposal	Only recycle completely empty containers. Remaining liquid materials should be brought to an authorised collection point for old paint/varnishes. Dried material residues can be disposed of as hard paint or domestic waste. Waste key no. 080112 according to the AVV waste directory regulation.
Handling guidelines	
Use	Before use, mix the material well / shake the container. In normal cases, apply evenly wet on wet without thinning down. On ultra-absorbent substrates, apply two coats wet on wet. The material application must harden the substrate evenly, though it should not result in a thick, glossy coat; if necessary, apply a sample coat. Do not use in direct sunlight, in strong winds and if there is a risk of rain or night frost.
Method of application	Can be applied with brush and spray devices
Airless application	Nozzle: 0.013" - 0.015" Spray pressure: 60 - 80 bar Spray angle: 20° - 50 ° Please note: Ensure even application of the primer in case of spray coating. Avoid formation of lustre effect due to overcoating. Protect adjoining surfaces, objects, etc. from drops or spray mist.
Application temperature lower limit	+ 5° C substrate and ambient temperature. Do not apply onto heated substrates.

Diessner Penetrating Primer (Diessner Tiefgrund)

Aqueous primer

Drying time

Paintable after approx. 8 hours at a temperature of + 23° C and 50% relative humidity. Considerably longer drying time at lower temperatures and/or higher humidity. During the drying time, the coat must be protected from moisture.

Cleaning the tools/ Airless equipment

Clean tools / equipment with water immediately after use.

Substrate preparation

Substrates must be solid, dry, free of dirt, blooming, discolouration, fungal growth, sintered layers, multi-grain layers and separating substances. Any old coats that are to be treated must be tested for their suitability, adhesion and stability. Pay attention to VOB (contracting rules for award of public works contracts), part C, DIN 18363, para. 3, the respective BFS datasheets and the technical datasheets 001/003.

We recommend creating sample areas before starting any work in order to test the effectiveness and quality of the surface.

Note

This technical information is compiled to the best of our knowledge and corresponds to our state-of-the-art application technology. However, you can only obtain non-binding advice as the working method in each individual case is dependent on the condition of the structure to be coated and can only be decided on the basis of the actual surface in question. Conditional exceptions are to be taken into account on site. Liability cannot be derived from the aforementioned information.

Due to the different substructure materials and the working conditions that are out of our control, we recommend conducting sufficient tests in each case to ensure the suitability of our products for the intended procedures and purposes.

All previous versions cease to apply with the publication of this technical data sheet.